



MASSETTO ADESIVO

Cement based screed
for thin-layer
adhering floor slabs



www.vimark.com



Strada Spartafino, 2
12016 Peveragno (CN)



ph. +39 0171 38.38.00
Fax +39 0171 33.93.95



info@vimark.com
www.vimark.com



MASSETTO ADESIVO

© Vimark S.r.l. May 2017 - Page 2 | 3

PRODUCT DESCRIPTION

MASSETTO ADESIVO is a ready to use cement based screed with normal setting and drying time, controlled shrinkage and good mechanical strength, designed for adhering floor slabs under tiles, terracotta, natural stone, parquet, resilient materials and decorative flooring systems. Specifically formulated with a high permeability to water vapour diffusion, ideal for screeds of 10 to 40 mm on traditional foundations, floor slabs, internal and external concrete. The product can be applied manually, with a continuous mixer or with traditional screed pumps.

COMPOSITION

MASSETTO ADESIVO is a pre-mixed screed based on special hydraulic binders, siliceous and limestone aggregates (selected and gauged according to specific grading curve) and special additives that improve the performance in terms of workability, adhesion to substrates and shrinkage control.

MIXING AND APPLICATION

The surfaces to be covered must be stable, dry, free of rising damp, cracks, dust, loose or friable parts. Before applying the product, prepare all vertical surfaces by applying the **COMPRIMIBILE PERIMETRALE** strip for the full height of the screed. Maintain any structural joints present on the floor base also in the thickness of the screed.

Mix the product by adding 3.5-4.0 litres approx. of clean water per 25 kg bag in a cement mixer. Pour the correct amount of water into the mixer and then add the powder. Mix the product for about 2'-3' minutes until smooth and free of lumps. Apply the product as a traditional screed, preparing the level guides and spreading the mixture. Compact and trowel the mixture until the surface is smooth and coplanar.

When laying screeds with variable thickness or however less than 35 mm, first apply on the clean base an adhesive grout composed by 1 part in weight of **MASSETTO ADESIVO**, 1 part in weight of **VIMARLATEX 883** and 1 part in weight of clean water. Spread a uniform and continuous layer of grout with a brush or trowel and then lay the screed with the "wet on wet" technique. Apply any level marker strips directly to the grout.

Apply **MASSETTO ADESIVO** as a traditional screed, which is compacted, struck off and finished by floating or mechanical machines, to obtain a coplanar and smooth surface. The use of reinforced fibreglass or metallic mesh in the screed is recommended.

COVERAGE

19 kg per m² per cm of thickness.

COLOUR

Grey.

PACKAGING

25 kg bags on disposable 1575 kg pallet (63 bags) protected by waterproof plastic wrap.

STORAGE

12 months from date of manufacture if stored in unopened original packaging in a dry and frost-free place.

RECOMMENDATIONS

Do not apply the product in temperatures below + 5°C or above + 35°C. Low temperatures and high humidity may affect drying time of the product. Avoid applying to frozen, dusty, unstable and inconsistent surfaces. Do not add more binders to product once it is ready for use. Do not add water to the product during the gripping phase. Always check the residual moisture of the screed before covering with tiles etc. Do not wet screed applied and protect surfaces from direct sun contact, rain and frost for the first 24 hours. Apply separation joints in correspondence to doorframes, openings or in the case of large areas. Do not add binders.

PRODUCT DATA

<i>Appearance</i>	Powder	
<i>Colour</i>	Grey	
<i>Powder volume mass</i>	~ 1650 kg/m ³	EN 1015-10
<i>Maximum aggregate size</i>	≤ 2.0 mm	

APPLICATION DATA

<i>Water content of mix</i>	14-18%	
<i>Mixture ratio</i>	1 bag + 3.5-4.5 l of water	
<i>Density of fresh mortar</i>	~ 1900 kg/m ³	EN 1015-6
<i>Minimum application temperature</i>	+ 5°C	
<i>Maximum application temperature</i>	+ 35°C	
<i>Pot life mixture</i>	> 60' minutes	EN 1015-9



Strada Spartafino, 2
12016 Peveragno (CN)



ph. +39 0171 38.38.00
Fax +39 0171 33.93.95



info@vimark.com
www.vimark.com



MASSETTO ADESIVO

© Vimark S.r.l. May 2017 - Page 3 | 3

PERFORMANCE DATA

<i>Minimum applying thickness</i>	≥ 10 mm (for floors subject to pedestrian traffic)
<i>Set to foot traffic</i>	> 24 ore (depending on weather conditions)
<i>Time before laying ceramic flooring</i>	> 7 days*
<i>Time before laying parquet flooring</i>	> 28 days*

* before laying the coatings always test the residual humidity using a Calcium Carbide hygrometer.

<i>Compressive strength</i>	≥ 16.0 N/mm ² C16	EN 13892-2
<i>Flexural strength</i>	≥ 5.0 N/mm ² F5	EN 13892-2
<i>Reaction to fire</i>	A1 _{fl} Class	EN 13501-1
<i>Böhme abrasive strength</i>	NPD	EN 13892-3
<i>Release of corrosive substances</i>	CT	EN 13892-2
<i>Water permeability</i>	NPD	EN 1062-3
<i>Vapour permeability</i>	NPD	EN 12086
<i>Sound insulation</i>	NPD	EN ISO 140-6
<i>Sound adsorption</i>	NPD	EN 12354-6
<i>Thermal resistance</i>	NPD	EN 12524
<i>Chemical resistance</i>	NPD	EN 13529

ACCORDING TO



EN 13813:2002

Cementitious screed material for internal use
CT-C16-F5

The management system has been certified according to:

EN ISO 9001
EN ISO 14001
BS OHSAS 18001

Product for professional use. The data and instructions in this data sheet are based on our best practical and laboratory experience. They refer to laboratory tests and should be considered indicative. In view of the different conditions of use and application, which depend on factors over which Vimark has no control (type of surface, environmental conditions, technical indications for fixing, etc.), those who use the product are responsible for ascertaining whether or not it is suitable for the intended purpose. Thus our warranty obligation merely covers the quality and fade-free characteristics of the actual product, and exclusively in relation to the aforementioned data. Vimark reserves the right to make technical modifications without prior notice. This technical data sheet voids and substitutes all previous editions. Updates will be published on the web site www.vimark.com.



Strada Spartafino, 2
12016 Peveragno (CN)



ph. +39 0171 38.38.00
Fax +39 0171 33.93.95



info@vimark.com
www.vimark.com